

FOREX PVC BOARD

Main Board Material	Material Composition	Polyvinyl chloride
	Color	White
	Technical Processing	Foam Process
	Water absorption	0.18% (Average)
	Elongation at Break	15%
	Charpy impact Strength	1.45 KJ/m ²
	Shore Hardness	50 Value
	Tensile strength	19.36MPa (Average)
	Flexural strength	9.97MPa (Average)
	Pulling Strength	12MPa (Average)
	Bending Strength	20MPa (Average)
	Compressive Strength	4MPa (Average)
Density	0.4g/cm ³ - 0.9g/cm ³	

Features	Soundproof, thermal insulation, damp-proof, mould proof,
	Eco-friendly, Waterproof, Non-toxic, Durable, Recyclable
Process	Digital Printing, Cutting, Moulding
Shelf Life	1 Year (Storage temperature 20 - 30°C, relative humidity of 45-55%),
	Keep away from Acid and Alkali
Applications	It is designed for Advertising, Decoration, Printing, Furniture, Construction, Sign
Packaging Details	PE BAGS FOR FREE/ CARTON BAGS/ WOODEN PALLETS.
Thickness	1mm -- 25mm
Size	1.22m x 2.44m, 1.56x3.05m, 2.05x3.05m

All above-released specifications and information are for guidance purposes only. Our policy of continuous improvement may result in changes. We therefore reserve the right to alter the specifications and the information at any time without notice.



All above-released specifications and information are for guidance purposes only. Our policy of continuous improvement may result in changes. We therefore reserve the right to alter the specifications and the information at any time without notice.

شركة النجم الرقمي للألات و المعدات

DIGITAL STAR MACHINERY AND EQUIPMENTS

Ibn Al Saqa | As Salhiyah Dist. | Riyadh - 12662