

LAMINATED FRONTLIT (G/M)

ITEM	UNIT	VALUE	TEST METHOD
Base Fabric	Denier	1000DX1000D	(High tenacity yarn)100%PES
Construction	Weaving/inch	9x9	/
Weight of fabric	Gsm/m ²	87±5	DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m ²	423±5	DIN53352 BS3424 Method5B
Total weight	Gsm/m ²	510±10	DIN53352 BS3424 Method5A
Thickness	mm	0.38±0.02	DIN EN ISO 2286-3
Width	cm	Up to 510	/
Tensile Strength	N/5cm	Warp	1350
		Weft	1150
Tensile Strength	N	Warp	160
		Weft	135
Adhesion	N/5CM	60	DIN53357 BS3425 Method9B
Temperature Resistance	°C	-20~70	DIN53357 BS3425 Method10
Lacquering	None		
Flammability	We can achieve: B1, B2, NFPA 701 etc.,		
LOW CADMIUM & HEAVY METALS	We can be applied for: Cadmium free (EN71-3) or Reach Compliance		
Conclusions & Announcements	<p>Declaration by MATRIX: Please choose MATRIX products suitably according to relative provisions or industrial standards. MATRIX bears the responsibility for the specified technical and performance data on this page only.</p> <p>MATRIX is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)</p>		
	Remarks: 'G' represents Glossy surface, "M" represents Matte surface, Glossy or Matte could be made as requirements		

* Our product enables us to have vivid colors and good printing quality. (Test printing is suggested before the printing job.)



All above-released specifications and information are for guidance purposes only. Our policy of continuous improvement may result in changes. We therefore reserve the right to alter the specifications and the information at any time without notice.